

Arrow 43 #Uses & Description

Arrow 43 is an asphalt saturated organic felt that is coated with a high quality asphalt coating. Arrow 43 is used as a base ply in a number of BUR applications and is non-perforated which makes it an ideal vapor retardant

Florida Approval # FL15067

Specifications

ASTM	D 2626
UL	TYPE 15
BREAKING STRENGTH, min lbf/in (kN/m)	
with fiber grain	35 (6.1)
across fiber grain	20 (3.5)
PLIABILITY, tested with 1/2" (13mm) radius	2 failures
MOISTURE, at time of manufacturing	2.0% max
MASS OF COATING AND SURFACING, lbs/100 ft² (g/m²)	18 (878), min
MASS OF DESATURATED FELT, lbs/100 ft² (g/m²)	5.2 (253)
THICKNESS OF DESATURATED FELT, in. (mm)	.025 (0.64) min
MASS OF SATURANT SOLUBLE IN TRIOCHLOROETHYLENE, lbs/100 ft² (g/m²)	7.2 (350)
MASS PERCENT OF MINERAL MATTER PASSING A 212-μm (no.70) SIEVE, based on the total mass of mineral-filled coating and mineral surfacing	60 %, max