

ASTM 15

Uses & Description

MSA ASTM 15 is an asphalt saturated organic felt designed for use as an underlayment with asphalt shingles in commercial and residential applications

Meets Florida Approval BFL # 15067



Specifications

ASTM	D 226 TYPE I
PLIABILITY, tested with 1/2" (13 mm) radius @ 77°F (25°C)	NO FAILURES
MOISTURE, at time of manufacturing	4.3%, max
LOSS ON HEATING, @221°F (105°C) for 5 hours	4%, max
NET MASS OF SATURATED FELT, lbs/100 ft²	11.5, min
MASS OF SATURANT, lbs/100 ft²	6.2, min
MASS OF DESATURATED FELT, lbs/100 ft²	5.2, min
ASH, desaturated felt mass	10%, max
SATURATION	120%, min

ASTM 30Uses & Description

MSA ASTM 30 is an asphalt saturated organic felt designed for use as an underlayment with asphalt shingles in commercial and residential applications

Meets Florida Approval BFL # 15067

Specifications

ASTM	D 226 TYPE II
PLIABILITY, tested with 1/2" (13 mm) radius @ 77°F (25°C)	NO FAILURES
MOISTURE, at time of manufacturing	4.1%, max
LOSS ON HEATING, @221°F (105°C) for 5 hours	4%, max
NET MASS OF SATURATED FELT, lbs/100 ft²	26.0, min
MASS OF SATURANT, lbs/100 ft²	15.0, min
MASS OF DESATURATED FELT, lbs/100 ft²	10.0, min
ASH, desaturated felt mass	10%, max
SATURATION	150% min